



Formulation

FURNITURE POLISH, AEROSOL

104320-1

INGREDIENTS:

	INGREDIENTS	% W/W
A	TEGOPREN® 7008 (Cetyl Dimethicone Copolyol)	0.5
	Paraffine wax 52/54 (Paraffine wax)	1.5
	Vestowax J 324 AM	1.5
	Shellsol TD (White Spirit, free of aromatic substance)	30.0
B	Water, demineralized	66.5

PROCESSING

Heat up ingredients 1 to 4 to 85 - 90°C. Add the melted wax-compound into hot water of same temperature (85-90°C). 78 parts of this polish are blended with 12 parts of repellent to fill the aerosol tins.

Disclaimer:

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Nutrition & Care GmbH

Rodenbacher Chaussee 4
63457 Hanau, Germany
Phone +49 6181 59-6338
Fax +49 6181 59-6338

info-household-care@evonik.com

www.evonik.com/household-care